



ELIOT

PERFORMANCE SPECIFICATIONS

		Abrasion	250,000+ DR
GENERAL SPECIFICATIONS Width 54"		Colorfastness to Crocking	Wet: 5 Dry: 5
		Seam Slippage	Fill: 62.4 Warp: 62.6
		Tensile Strength	Fill: 96
Weight	18-19 oz/linear yard		Warp: 118
Surface Composition	95% High Solid Polyurethane (Polycarbonate),	Tear Strength: Tongue Tear	Fill: 12.1 Warp: 10.4
	5% Silicone	Colorfastness to Light	200 Hours
Substrate Composition	100% Polyester	Cold Crack	-20°F
Gauge	0.040	Hydrolysis Resistance	15 weeks
Thickness	1.00 mm	Anti-Bacterial	Passes
		Anti-Microbial	Passes
FLAME RETARDANCY SPECIFICATIONS Bleach Resistant		Yes – 20% Dilution	
		Stain Resistant	Yes
CAL-TB 117-2013	Passes	Denim Dye Resistant	Yes
NFPA 260	Passes	Ink Resistant	Yes
UFAC Class 1	Passes	Sulfide Stain Resistant	Yes

REDUCED ENVIRONMENTAL IMPACT

This product does not pose any exposure risks associated with the chemicals in Prop $\mathbf{65}$

Phthalate Free

Lead Free

BPA Free/TRIS Free/Formaldehyde Free

Does not contain Conflict Minerals

Does not contain Flame Retardant Chemicals

Does not contain Anti-Microbial/Anti-Bacterial Chemicals

PVC Free

CAB 2998 Compliant

RECOMMENDED APPLICATIONS









WORKSPACE HEALTHCARE HOSPITALITY RESTAURANT

A ★ *O* ***** *M**

*ACT® Registered Certification Marks

|+|

FINISHES

